

LAMINATED FRONTLIT WHITE/BLACK (G/M)

ITEM	UNIT	VALUE	TEST METHOD	
Base Fabric	Denier	840DX840D	(High tenacity yarn)100%PES	
Construction	Weaving/inch	9x9	/	
Weight of Fabric	Gsm/m ²	75±5	DIN53352 BS3424	Method5B
Weight of PVC	Gsm/m ²	365±5	DIN53352 BS3424	Method5B
Total weight	Gsm/m ²	440±10	DIN53352 BS3424	Method5A
Thickness	mm	0.35±0.02	DIN EN ISO 2286-3	
Width	cm	Up to 510	/	
Tensile Strength	N/5cm	Warp	1350	DIN53352 BS3424
		Weft	1200	
Tensile Strength	N	Warp	125	DIN53356 BS3424
		Weft	100	
Adhesion	N/5cm	60	DIN53357 BS3425	Method9B
Temperature Resistance	°C	-20~70	DIN53357 BS3425	Method10
Lacquering	None			
Flammability	We can achieve: B1, B2, NFPA701, etc.			
Low Cadmium & Heavy Metals	We can be applied for : Cadmium free (EN71-3) or Reach Compliance			
Conclusions & Announcements	Declaration by MATRIX: Please choose MATRIX products suitably according to relative provisions or industrial standards. MATRIX bears the responsibility for the specified technical and performance data on this page only.			
	MATRIX is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)			
	Remarks: 'G' represents Glossy surface, "M" represents Matte surface, Glossy or Matte could be made as requirements			

* Our product enables us to have vivid colors and good printing quality. (Test printing is suggested before the printing job.)



All above-released specifications and information are for guidance purposes only. Our policy of continuous improvement may result in changes. We therefore reserve the right to alter the specifications and the information at any time without notice.