

COATED MESH WITH LINER

ITEM	UNIT	VALUE	TEST METHOD	
Base Fabric	Denier	1000DX1000D	(High tenacity yarn)100%PES	
Construction	Weaving/inch	12x12	/	
Weight of MESH	Gsm/m ²	370±20	DIN53352 BS3424 Method5B	
Weight of PVC Liner	Gsm/m ²	100	DIN53352 BS3424 Method5B	
Total weight	Gsm/m ²	400±20	DIN53352 BS3424 Method5A	
Width	cm	Up to 320	/	
Tensile Strength	N/5cm	Warp	1250	DIN53352 BS3424
		Weft	1100	
Tensile Strength	N	Warp	235	DIN53356 BS3424
		Weft	225	
Air Permeability	mm/s	2649	GB/T 2410-2008	
Light Transmission	/	37%	GB/T 5453-1997	
Temperature Resistance	°C	-20~70	DIN53357 BS3425 Method10	
Lacquering	None			
Flammability	\			
LOW CADMIUM & HEAVY METALS	\			
Conclusions & Announcements	<p>Declaration by MATRIX: Please choose MATRIX products suitably according to relative provisions or industrial standards. MATRIX bears the responsibility for the specified technical and performance data on this page only.</p> <p>MATRIX is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)</p>			

* Our product enables us to have vivid colors and good printing quality. (Test printing is suggested before the printing job.)



All above-released specifications and information are for guidance purposes only. Our policy of continuous improvement may result in changes. We therefore reserve the right to alter the specifications and the information at any time without notice.